

EXTREME BOND

A 2-part toughened structural acrylic for bonding



For bonding wood, glass, metal, plastic and composites.

What is a toughened acrylic?

Extreme Bond is a 2nd generation acrylic adhesive. This has been designed to combine high-shear strength & excellent temperature resistance with additional qualities of a rubber toughened adhesive.

When to use Extreme Bond

When maximum strength is required. With metal fabrications requiring shock resistance or flexibility. When bonding dissimilar materials with different coefficients of expansion and where a short jig time is required.

Key features and benefits of Extreme Bond

Adhesion to a wide range of substrates.

Fast cure at room temperature.

Can be used with or without nozzle.

High shear and peel strength

Good impact strength.

Good chemical resistance.

3) Alternatively apply a thin layer of resin on one component and hardener on the other.

4) Assemble components and clamp.

5) Maintain pressure until handling strength is achieved. The time required will vary according to the joint design and surfaces being bonded.

6) Allow 24 hours for adhesive to fully cure. Accelerated cure times may be achieved by heating.

Directions for use

1) Surfaces must be clean, dry and grease-free. If using a cleaning solvent, allow 3-4 minutes to fully evaporate before applying adhesive. N.B. Some metals such as aluminium, copper and its alloys will benefit from light abrasion with emery cloth (or similar) to remove any oxide layer.

2) Apply a thin bead of adhesive pre-mixed through a static mixer nozzle. If no mixing nozzle is being used, make sure one component is extruded on top of the other (not side by side).

Storage & Handling

Storage Temperature 2 to 7°C (35 to 45°F)

Health and Safety:

Before use, it is important that you have read and understood the product label and Safety Data Sheet for each component of this product. These are also available on our website, www.img-limited.co.uk.

TERO TECH Riverside Industrial Estate, Fazeley, Tamworth, Staffordshire, B78 3RW.
Head Office, Warehousing and Distribution: Tel: 01827 283322, Fax: 01827 250143. Telesales: 01270 611031

The **IM Group** utilizes a process of continuous product improvement for all of our products. While we do strictly adhere to our products' specifications, we routinely implement product improvements. Therefore, please contact us for our most current product specifications. IM Group warrants the quality of this product when used according to directions. User shall determine suitability of product for use and assumes all risk. The seller will not accept liability for more than product replacement.

Trademarks: **TECH TECH** is a registered trademark and subsidiary of **IM Group**.

